

CONSTRUCTION	Axminster	
PILE YARN	100% Wool	
BACKING COMPONENTS	Jute, Co/Pe, Polypropylene	
NO OF SHOTS	N/A	
PILE WEIGHT ± 5%	1133 g/m²	
TOTAL CARPET WEIGHT ± 10%	2557 g/m ²	Axminster Carpets Ltd Axminster, Devon, EX13 5PQ
NO OF FRAMES	N/A	16
PILE HEIGHT ± 5%	7.9mm	
GAUGE/PITCH	31.5 per 10cm (8 per inch)	Axminster Woven
ROWS	27.6 per 10cm (7 per inch)	
TUFT DENSITY ± 5%	992.25 per 10cm ² (64 inch ²)	Reaction to fire Class C_{fl} - S1 (see EN 14041, Table 3)
WIDTH ± 1.25%	3.66 metre 12 foot	Slipperiness NPD
		Formaldehyde E1
FLAMMABILITY	Cfl- s1	
ISO 9239/1:2002		
SLIPPERINESS	NPD	
FORMALDEHYDE	E1	
SUITABILITY	Extra Heavy Domestic ;	
	Commercial	

TECHNICAL SPECIFICATION - Hazy Days

GENERAL INFORMATION

COLOUR MATCH	Due to batch variations in dye lots, an exact match for colour between different	
	widths, qualities and samples cannot be guaranteed.	
FADING	Photobleaching is caused when the natural yellow pigment which gives wool its creamy colour reacts with ultra-violet light making the wool appear much whiter. Although every care is taken to ensure our dyes meet strict requirements, carpets, as with other natural textiles, cannot be dyed absolutely fast to light and with the increase in UV rays, carpets will fade when subjected to daylight. Normal wear and light soiling will also give the appearance of fading and both effects are obviously	
	beyond the control of the manufacturer.	
FITTING	All carpets should be professionally fitted in accordance with BS5325	
SHADING, PILE PRESSURE OR PILE	These are natural characteristics of all cut pile fabrics. This is especially noticeable on	
REVERSAL	plain and tonal shades or open ground designs and is the result of pressure causing a change in the direction of the pile, giving light and dark patches, accentuated by room lighting. This does not affect the quality or life of the carpet and is not a fault of manufacture. The regular use of an upright cleaner will help to alleviate this effect.	
SPECIFICATION AMENDMENTS	The Company is continually striving to improve our products and reserves the right to substitute raw materials as necessary.	