


### TECHNICAL SPECIFICATION – 8104979

|                                 |                                                        |
|---------------------------------|--------------------------------------------------------|
| CONSTRUCTION                    | Axminster                                              |
| PILE YARN                       | 80% Wool, 20% Nylon                                    |
| BACKING COMPONENTS              | Jute, Co/Pe, Polypropylene                             |
| NO OF SHOTS                     | N/A                                                    |
| PILE WEIGHT ± 5%                | 1733 g/m <sup>2</sup>                                  |
| TOTAL CARPET WEIGHT ± 10%       | 3012 g/m <sup>2</sup>                                  |
| NO OF FRAMES                    | N/A                                                    |
| PILE HEIGHT ± 5%                | 7.9mm                                                  |
| GAUGE/PITCH                     | 31.5 per 10cm (8 per inch)                             |
| ROWS                            | 39.4 per 10cm (10 per inch)                            |
| TUFT DENSITY ± 5%               | 1241 per 10cm <sup>2</sup> (80 per inch <sup>2</sup> ) |
| FLAMMABILITY<br>ISO 9239/1:2002 | Cfl- s1                                                |
| SLIPPERINESS                    | NPD                                                    |
| FORMALDEHYDE                    | E1                                                     |
| SUITABILITY                     | Heavy Commercial                                       |



Axminster Carpets Ltd  
Axminster, Devon, EX13 5PQ  
16

**EN 14041**  
8104979  
Axminster Woven 80% Wool 20% Nylon  
Carpet for use in Buildings (EN1307)

**Reaction to fire** Class C<sub>fl</sub> - S1 (see EN 14041, Table 3)

**Slipperiness** NPD

**Formaldehyde** E1

### GENERAL INFORMATION

|                                         |                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                        |
|-----------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| COLOUR MATCH                            | Due to batch variations in dye lots, an exact match for colour between different widths, qualities and samples cannot be guaranteed.                                                                                                                                                                                                                                                                                                                                                                                                                   |
| FADING                                  | Photobleaching is caused when the natural yellow pigment which gives wool its creamy colour reacts with ultra-violet light making the wool appear much whiter. Although every care is taken to ensure our dyes meet strict requirements, carpets, as with other natural textiles, cannot be dyed absolutely fast to light and with the increase in UV rays, carpets will fade when subjected to daylight. Normal wear and light soiling will also give the appearance of fading and both effects are obviously beyond the control of the manufacturer. |
| FITTING                                 | All carpets should be professionally fitted in accordance with BS5325..                                                                                                                                                                                                                                                                                                                                                                                                                                                                                |
| SHADING, PILE PRESSURE OR PILE REVERSAL | These are natural characteristics of all cut pile fabrics. This is especially noticeable on plain and tonal shades or open ground designs and is the result of pressure causing a change in the direction of the pile, giving light and dark patches, accentuated by room lighting. This does not affect the quality or life of the carpet and is not a fault of manufacture. The regular use of an upright cleaner will help to alleviate this effect.                                                                                                |
| SPECIFICATION AMENDMENTS                | The Company is continually striving to improve our products and reserves the right to substitute raw materials as necessary.                                                                                                                                                                                                                                                                                                                                                                                                                           |